



Navigation



Extrusion 1-0-Wiki Pages

- [Main Page](#)
- [Best Papers](#)
- [Book Reviews](#)
- [Consultants Corner](#)
- [Extruder Software](#)
- [Extrusion Hints](#)
- [Safety](#)
- [Shop Tools](#)
- [Sponsors](#)
- [Technical Articles](#)

Search the Wiki

  »

Viewing/Creating

- [Random Page](#)
- [Create a new Page](#)
- [All Pages](#)
- [Categories](#)

Account Management

- [Login/Logout](#)
- [Language Selection](#)
- [Your Profile](#)
- [Create Account](#)

Administration

- [Administration](#)
- [File Management](#)

Brought to you by:

The SPE Extrusion Division
Board of Directors



Cool Dryer Return Air

Modified on Monday, 02 February 2015 01:01 PM by [mpieler](#) Categorized as [Extrusion Hints](#) 
(10) » [Pull the Screw](#) » [Unmixed Polymer Gels](#) » [Cool Dryer Return Air](#)

Cool Dryer Return Air

Vol. 26 #2, September 1999 and Vol. 26 #3, December 1999


When using a dehumidifying dryer to pre-dry moisture sensitive hygroscopic resins, it is important to monitor the dryer's return air temperature carefully. If the return air temperature climbs above 150°F, the moisture loading capacity of the dehumidifying dryer will be reduced below its design specifications. A return air temperature of 180°F will reduce the dryer's moisture loading capacity by 50%. It will also greatly shorten the life of the dryer's blower.

- Pete Stoughton, Conair

See also:

- [Closed loop dryer](#)
- [Dryer inlet air](#)
- [Installing a dehumidifying drying system](#)

Return to [Extrusion Hints](#)

Some of the icons were created by [FamFamFam](#) .